

CTM POTTERS SUPPLIES

SPEC SHEET

CUPROUS OXIDE

Appearance: -	Red Powder
Stability: -	The cuprous Oxide will lose not more than 2% of its total reducing power when exposed to an atmosphere of air with relative humidity of 95% at 100°F for a period of 72 hours.
Bulk Density: -	1.3 – 1.4g/ml

Chemical Specification

Cuprous Oxide (Cu₂O)	99%
Total Copper	87%
Total reducing Power (T.R.P)	99%
Metallic Copper	0.014%
Stability Loss	0.24%