

Technical Data Sheet

LoStone: Sea-Mist



Throwing



Modelling



Casting



Firing Range: 1060-1220°C

Cone 04 to Cone 6 (maximum)



Colour: Pale grey with blue undertones



Texture: Smooth



Bag Size: 10kg

Fired at

1220°C

1200°C

1180°C

1160°C



1140°C

1120°C

1100°C

1080°C

1060°C



Chemical Analysis %	
Chemical	%
SiO ₂	64.93
TiO ₂	1.06
Al ₂ O ₃	21.95
Fe ₂ O ₃	0.61
CaO	0.42
MgO	0.24
K ₂ O	3.35
Na ₂ O	1.84
LOI	5.85

% Total Contraction	
1100°C	8.5
1200°C	12.0

Thermal Expansion	
% at 500°C	0.351
Coefficient of Expansion C.O.E (x 10 ⁻⁶)	7.3

This technical information is only a guide, established from the characterisation and analysis of representative samples, and from routine production averages. Product characteristics are subject to modifications.