

TECHNICAL DATA SHEET

PRODUCT	
RED TERRACOTTA GROGGED MARL	Dried and pulverised Etruria Marl that casts well due to medium sized grog added and is suitable for large items like garden pots or urns. A beautiful rich terracotta coloured clay, when fired to 1080°C. Fired range 1080°C to 1180°C.

CHEMICAL ANALYSIS (MEAN VALUES. THESE DO NOT REPRESENT A SPECIFICATION.)		
Silicon Oxide	SiO ₂	52.6
Titanium Oxide	TiO ₂	1.33
Aluminium Oxide	Al ₂ O ₃	23.1
Ferric Oxide	Fe ₂ O ₃	10.7
Lime	Ca(OH) ₂	0.3
Magnesium Oxide	MgO	0.57
Potassium Oxide	K ₂ O	2.12
Soda	NaHCO ₃	0.33
Phosphorus Pentoxide	P ₄ O ₁₀	0.12
Chromium Sesquioxide	Cr ₂ O ₃	0.02
Manganic Oxide	MnO ₂	0.27
Zirconia	ZrO ₂	0.02
Barium Oxide	BaO	0.11
Strontia	SrO	0.01
Loss of Ignition	LOI	7.96

Product Availability
The products are available in 25kg Paper Bags, big bags and bulk.